



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

REC'D 01 SEP 2003

WIPO PCT

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02012031.7

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk



Anmeldung Nr:
Application no.: 02012031.7
Demande no:

Anmeldetag:
Date of filing: 31.05.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Carbon Application Technology Ltd.
Unit 2A, Hixon Industrial Estate,
Church Lane
Staffordshire ST18 0YP
GRANDE BRETAGNE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Fiber reinforced filter for molten metal filtration and method for producing such filters

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

B01D/

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR

EPO - Munich
94
31 Mai 2002

May 29, 2002
021492ep/HPJ

5

10 **FIBER REINFORCED FILTER FOR MOLTEN METAL FILTRATION
AND METHOD FOR PRODUCING SUCH FILTERS**

15 The present invention relates to a fiber reinforced ceramic filter for
molten metal filtration that comprises a bonded network of graphitized
carbon and a method for producing such filters.

20 For the processing of molten metals it is desirable to remove exogenous
intermetallic inclusions such as from impurities of the raw materials,
from slag, dross and oxides which form on the surface of the melt and
from small fragments of refractory materials that are used to form the
chamber or vessel in which the molten metal melt is formed.

25 Removal of these inclusions forms a homogenous melt that insures high
quality of products especially in the casting of steel, iron and aluminum
metals. Currently, ceramic filters are widely used due to their high
ability to withstand extreme thermal shock due to their resistance to
chemical corrosion and their ability to withstand mechanical stresses.

The production of such ceramic filters generally involves the mixing of ceramic powder with suitable organic binders and water in order to prepare a paste or slurry. The slurry is used to impregnate a polyurethane foam which subsequently is dried and fired at a temperature in the range of from 1000 to 1700 °C. By this treatment the combustible material is burned off during sintering to produce a porous body. US-A-2,360,929 and US-A-2,752,258 may serve as examples for the common procedure.

Also, an open pore filter that instead of a random distribution of irregular interconnecting passages consists of a series of parallel ducts passing through the material as generally being made by hydraulic pressing a damp ceramic powder and organic binder into a mold containing perpendicular pins. A perforated structure is thus obtained which can be in the form of a disk or block. The perforated article is then fired at a temperature in the range of from 1000 to 1700 °C depending on the final application to produce a perforated disc. During firing a ceramic and/or glassy bond is developed.

WO 01/40414 A describes the use of pressurized mould. This patent depends on regulating the pressure inside the mould to obtain porous structure. Also the porosity in this case is not fully open. The claim of filtration usage is one of many usage and there is no prove that the filter was ever actually used to metal filtration. Also only aluminum was mentioned for filtration since such filter is too weak for steel filtration. The patent describes only a carbon filter without any ceramic. The process of making the filter is based on regulating the pressure inside the mould. This process is difficult to control.

US-A-4,514,346 uses phenolic resin to react with silicon at high temperature to form silicon carbide. There is no carbon bonding involved. This patent is for making porous silicon carbide only. Temperature in excess of 1600 °C is used to obtain silicon carbide. The process is non-aqueous. The porosity obtained from this process is closed porosity which has no use in filtration requiring open porosity.

GB-A 970 591 deals with making high density low permeability graphite articles. It uses an organic solvent, namely furfuryl alcohol as solvent and not water. Binder in the form of pitch is used at 25 % with no ceramic at all. Final heating is in excess of 2700 °C. The porosity is closed porosity rather than open porosity.

US-A-3,309,433 describes a method for manufacturing high density graphite. It uses hot pressing as a means to obtain high density graphite articles for nuclear applications. It used special material called Dibenzanthrone to bind the graphite. It has no useful application in metal filtration field. It does not use any ceramic in the process. It uses high temperature of up to 2700 °C.

EP 0 251 634 B1 describes an appropriate process for making defined porous ceramic bodies having smooth walled cells formed by the pore formers, and pores with round edges, which interconnect the cells.

US-A-5,520,823 relates to filters for aluminum only. The bonding is obtained using borosilicate glass. Firing is carried out in air and a considerable amount graphite would be lost due to the oxidation by air.

Filters used for aluminum filtration are usually fired at around 1200 °C while those intended for the use of iron are fired at temperatures of 1450 °C and for steel at above 1600 °C.

5 Despite their wide spread use for metal filtration ceramic filters of the above mentioned types have several drawbacks that limit their applicability:

10 1. Ceramic filters, although preheated, tend to be clogged by freezing particles on the first contact with the molten metal. For this purpose usually superheated molten metal that is metal at a temperature of about 100 °C over liquidus temperature is used for casting to prevent clogging of the filters. This practice is extreme
15 wasteful in terms of energy and cost and any improvement that reduces processing temperature of the molten metal is of great benefit. Carbon coatings have been applied in the prior art on the surface of ceramic filters to reduce the thermal mass of the part that comes into direct contact with the molten metal.

20 Also an exothermically reacting thermite material applied to a carbon-coated surface of the ceramic filter has been proposed by EP 0 463 234 B1. The latter solution, while reducing the temperature necessary for the flow of the molten metal, adds to the cost of production of the filters and very narrowly limits the applicability as the thermite coating has to
25 be in compliance with the type of molten metal for which it is used.

Anyway, both carbon and thermite coating serve in overcoming the drawback of high thermal mass of the ceramic filter while the challenge of several more disadvantages is not met.

30

2. Ceramic and glassy type bonds tend to soften and creep at high temperature which very often results in erosion of the filter and subsequent contamination of the melt.

3. Cracking due to thermal shock or chemical (reductive) corrosion by the hot metal melt is a problem often encountered with ceramic and glass bonded filters.

4. The need for extremely high firing temperatures, especially in the case of ceramics intended for steel filtration, is a severe drawback of conventional ceramic filters which is even worse when the need for high cost - ceramic raw material is considered.

5. In addition, the use of zirconia with its relatively strong background radiation is hazardous and should be avoided.

15

Co pending EP 01121044.0, filed on 01. September 2001, relates to a ceramic filter suitable for molten metal filtration comprising a bonded network of graphitized carbon. Carbon bonded ceramics in general are weak and suffers from low mechanical strength. The carbon bonded filters according to this reference have a limited mechanical strength which causes problems during transportation and usage and limit the capacity of the filters in withstanding the pressure of molten metal on it.

20

Also these filters are friable and tends to break into bits which falls in the mould prior to casting causing contamination of the casting.

25

The object of the present invention is thus to provide a filter for metal filtration which improves the mechanical strength and stiffness.

In the ceramic filter suitable for molten metal filtration according to the present invention a three dimensional network of graphitizable carbon bonding and fibers is used to bind ceramic powder.

5 In a first embodiment, the invention relates to a ceramic filter suitable for molten metal filtration comprising a bonded network of graphitized carbon and fibers.

10 The term "graphitizable" means that the carbon bonding obtained by pyrolysis of the carbon precursor can be converted into a graphite like bonding on heating to a higher temperature in the absence of air. Graphitizable carbon is distinguished from that of a glassy carbon by the fact that it is impossible to convert glassy carbon to a graphite like bond no matter how high temperature it was heated to.

15 Carbon bonding of this type exhibits the following advantageous features:

- Significantly cheaper to produce.
- Firing can be carried out at much lower temperature in order to
20 develop the full carbon bonding network from the carbon bond precursor. In general the filters have to be fired at a temperature in the range of from 500 °C to 1000 °C.
- Significantly lower superheat is required.
- Low thermal mass.
- 25 - Better thermal shock resistance.
- Contamination free.

30 The carbon bonded filters according to the present invention exhibit a relatively low thermal mass. A result of this is that there is no need to overheat the metal to be filtered which reduces energy consumption.

During the continuous work to improve the quality and the performance of carbon bonded filters, the inventor now discovered that adding up to 20% by weight of fibers to the filter recipes contribute to a significant improvement in the performance of the filters. The improvement is mainly due to increase mechanical strength, improve stiffness, higher impact resistance and better thermal shock. The improvement is manifest it self by increase filtration capacity, better mechanical integrity and less contamination to the steel casting. Due to the outstanding mechanical strength of the carbon bonding in combination with fibers at high temperature no softening or bending can take place during the process of metal casting. This contributes to an even cleaner metal cast.

Graphitizable carbon bonded filters further including fibers according to the present invention offer the following advantages compared with glassy carbon bonded filters:

- High oxidation resistance
- High mechanical strength
- High impact resistance
- Low microporosity
- Low specific surface
- Structural flexibility
- Non-brittle behavior
- Economical use.

For optimal performance the graphitized carbon that constitutes the bonded network according to the present invention should be present in an amount up to 15 % by weight of the filter, preferably up to 10 % by

weight, even more preferred in an amount of at least 2 % by weight up to 5 % by weight.

Traditionally, fibers are added to ceramic and composite materials in order to improve mechanical strength and gives stiffness to the articles. These fibers could be either metal fibers, organic fibers such as polyester fibers, viscose fibers, polyethylene fibers, polyacrylonitrile (PAN) fibers, aramid fibers, polyamide fibers, etc., or ceramic fibers such as aluminosilicate fibers, alumina fibers or glass fibers, or carbon fibers which consist of 100% carbon. All these types of fibers are used to a different degrees in ceramic to give added advantaged to the properties of ceramic such as high mechanical strength, high impact resistance and better thermal shock.

The inventor has found that addition of any of the types of fibers to the carbon bonded filters of the prior art causes a significant improvement in the mechanical strength of the filters as well as improvement in the impact resistance and thermal shock. The improvement in strength could be as much as three time (i.e. from 0.5 MPa to 1.5 MPa). Impact resistance and thermal shock resistance also increase accordingly. As a result of this improvement, the carbon filters can now at least double their filtration capacity. For example a carbon filter with 100mm x 100mm x 20mm which have a normal capacity of 100 kg filtration of steel. The same filter but with 5% added ceramic filters has a capacity to filter 200 kg of steel. In particular ceramic fibers and carbon fibers do not change their physical properties when they are incorporated in the filter due to their thermal stability. Organic fibers, on the other hand are converted during firing of the filters to carbon fibers (i.e. They undergo a pyrolysis process). This is considered to be beneficial.

30

The inventor has found that the beneficial effect of the addition of fibers depends on the amount of fibers added, length of the fibers, nature and type of fibers added. The higher the level of fibers added the stronger the filter become. However very high level of fibers is not desirable because it has a negative effect on the rheology of the slurry. Best results are obtained from incorporating carbon fiber followed by Ceramic fibers . On the other hand, carbon fibers are the most expensive while organic fibers are the cheapest. Organic fibers are the most economic to use since they are added at much lower level than either carbon or ceramic fibers(less than 2%). However, organic fibers interferes with the rheology of the slurry more than the ceramic or the carbon fibers. The form of fibers are either chopped or bulk fibers to be added during mixing of the filter ingredients. No extra mixing technique is required.

The filters according to the present invention preferably contain 0.1 to 20 % by weight, in particular 1 to 10 % by weight of said fibers, more particularly 5%.

The fibers used according to the present invention preferably have a length from 0.1 mm to 5 mm.

In one embodiment of the present invention the carbon bonded ceramic filters are produced in a first process comprising the steps:

- a) impregnating a foam made of thermoplastic material with a slurry containing fibers, a graphitizable carbon bonding precursor, ceramic powder, and optionally other additives,
- b) drying, optionally followed by one or two coatings of the same slurry in order to increase the mass, followed by final drying,

c) firing the impregnated foam in non-oxidizing and/or reducing atmosphere at a temperature in the range of from 500 to 1000 °C, in particular from 600 °C to 700 °C,

5 whereby the carbon bonding precursor is converted at least partially or fully to a bonded network of graphitized carbon.

In this process the thermoplastic material used for the foam to be impregnated with the slurry preferably contains or consists of polyurethane.

10 It is advantageous to mix fibers, carbon bonding precursor prior to impregnating the foam with ceramic powder, water, organic binder, and additives to control the rheology, which in one embodiment of the invention may be present in an amount of up to 2 parts by weight, preferably in a range of from 0.1 to 2 parts by weight.

15

In another embodiment of the present invention a second type of carbon bonded ceramic filter is produced by a process comprising the steps

20 a) pressing a semi-damp mixture comprising fibers, ceramic powder and a graphitizable bonding precursor, and optionally other additives in a hydraulic press,

b) pressing to obtain a perforated article in the shape of a disk or a block,

25 c) firing the perforated article in non-oxidizing and/or reducing atmosphere at a temperature in the range of from 500 °C to 1000 °C, in particular from 600 °C to 700 °C,

whereby the carbon bonding precursor is converted partially or fully to a bonded network of graphitized carbon.

The source of the carbon bond, that is the carbon bond precursor is preferably high melting pitch (HMP) because it offers optimal properties with respect to workability, cost and product quality. However, it must be noted that other carbon bond precursors can also be used to produce
5 carbon bonded materials, such as synthetic or natural resins and sinterable carbon as long as it is graphitizable and converted to a bonded network of graphitized carbon upon firing according to the present invention. Thus, synthetic resin binders that form a glassy carbon which cannot be converted to graphite may not be considered as
10 carbon bond precursors as the product suffers from low oxidation resistance, low mechanical strength, high brittleness and lower heat resistance.

Also, for economical as well as ecological reasons the carbon bond
15 precursor should be compatible with water. However, organic-solvent based carbon bonding precursors may be used as well.

In further embodiments these processes use a slurry (for the production of a carbon bonded ceramic filter of the first type) or a semi-damp
20 mixture (for the production of the carbon bonded ceramic filter of the second type) that comprises:

fibers in the range of 0.1 to 20 % by weight,
a graphitizable carbon bonding precursor in the range of from 2 (5) to
15 (25) parts by weight,
25 ceramic powder in the range of from 0 (20) to 95 (80) parts by weight,
anti-oxidation material in the range of from 0 to 80 parts by weight,
graphite in the range of from 0 to 90 parts by weight,
organic binder in the range of from 0 to 10, in particular 0.2 to 2 parts
by weight and,

dispersion agent in the range of from 0 to 4, in particular 0.1 to 2 parts by weight.

5 Water is added in a quantity as required. For the purpose of slurry-preparation, 20 to 70 parts by weight are necessary depending on the nature of the ceramic filler materials. For the semi-damp mixture used for pressing, water is necessary in an amount of from 2 to 10 parts by weight, depending of the nature of the ceramic filler materials.

10 The ceramic powder may comprise zirconia, silica, alumina, brown fused alumina, magnesia, any type of clay, talcum, mica, silicon carbide, silicon nitride and the like or any mixture thereof. Graphite may also be used as a substitute for ceramic powder.

15 Preferred anti-oxidation materials according to the present invention are metallic powder such as steel, iron, bronze, silicon, magnesium, aluminum, boron, zirconium boride, calcium boride, titanium boride and the like, and/or glass frits containing 20 to 30 % by weight of boric oxide.

20

Organic binders that are preferred according to the present invention are green binders such as polyvinyl alcohol (PVA), starch, gum arabic, sugar or the like or any combination thereof. These binders may be added to improve the mechanical properties of the fillers during
25 handling prior to firing. Starch and gum arabic may also be used as thickening agent.

Preferred dispersion agents according to the present invention are Despex®, ligninsulphonate or the like, or any combination thereof which
30 help to reduce the water level in the slurry and improve the rheology.

In a further embodiment of the present invention the slurry or semi-damp mixture may comprise a plasticizer such as polyethylene glycol (preferred molecular weight: 500 to 10000) in the range of from 0 to 2 parts by weight, preferably 0,5 to 1 part by weight and/or

5 an anti-foam agent such as silicon anti-foam in the range of from 0 to 1 part by weight, preferably 0,1 to 0,5 parts by weight.

The invention is further illustrated by the following examples:

10

Examples:

As graphitizable high melting pitch (HMP) a coal-tar pitch was used
15 having a glass transition temperature of 210 °C, a coking value of 85 %, an ash value of 0,5 % and which was available as a fine powder.

In all examples the resultant mixture was fired in inert atmosphere at a temperature in the range of from 600 °C to 900 °C for 20 to 120 min at
20 a heating rate in the range of from 1 °C/min to 10 °C/min.

A: Filters according to the first type:

Example 1

25

A polyurethane foam was cut to the required size and impregnated with a slurry containing 70 g of un-chopped alumina silicate ceramic fibers, 70 g of said high melting pitch powder, 1000 g of ceramic powder (calcined alumina), 70 g of a dispersant(ligninsulphonate), 4 g of a
30 thickening agent(starch) and 270 g of water.

The filter was either impregnated manually or by a machine containing rollers used for this purpose. After impregnation the filter was dried using hot air and/or a microwave drier. The coating was applied by a spraying air gun. The filter was dried once more and transferred to a firing furnace with reducing or non-oxidizing atmosphere. The furnace was heated at a rate from 1 °C/min to 10 °C/min depending on the composition of the slurry, size of the filter, size of the furnace etc.

10 These filters have a strength of up to 1.5 MPa. During field trials it was found that no superheat is required when using these filters since extra heat was generated upon contact of molten metal with the filter (exothermic reaction).

Also heating these filters to a temperature above 1500 °C results in forming a fiber reinforced graphite like bonding. Although such treatment would improve the overall properties of the filter, it is not required for the purpose of molten metal filtration.

Example 2

20

Example 1 was repeated with the same recipe but using 70 g of 0.2mm chopped carbon fibers to replace aluminosilicate fibers. The result was even better strength of up to 2 MPa.

25 Example 3

Example 1 was repeated with the same recipe but using 2% by weight of 0.250 mm polyester fibers to replace aluminosilicate fibers. The result was a strength of higher than 2 MPa.

30

B: Filters according to the second type:

Example 4

- 5 A mixture of 50 g of aluminosilicate ceramic fibers , 70 g of said high melting pitch powder, 900 g of ceramic powder (calcined alumina), 100 g of graphite powder, 20g PVA binder and 60 g of water was prepared in a Hobart or Eirich mixer. The aim of the mixing process was to make a semi-damp and homogenous mixture. A predetermined weight of the
- 10 mixture was placed in a steel mold which contained vertical pins. Pressing the mix produced a perforated article. This perforated article was then removed form the mold, dried and fired in a non-oxidizing or reducing atmosphere at a temperature of 700 °C for 1 h with a heating rate of 2 °C/min. The strength of the pressed filters increased from 7
- 15 MPa to 10 MPa due to the addition of fibers.

Example 5

- Example 4 was repeated with the same recipe but using 70 g of 0.2 mm
- 20 chopped carbon fibers to replace aluminosilicate fibers. The result was a strength of up to 12 MPa.

Example 6

- 25 Example 4 was repeated with the same recipe but using 2% by weight of 0.250 mm polyester fibers to replace aluminosilicate fibers. The result was a strength of higher than 15 MPa.

- The fiber reinforced graphitizable carbon bonded perforated filter was
- 30 used in a field trial to filter molten steel. It was found that the filter did

not require molten metal superheat since it generated heat on contact of molten metal with the filter which was enough to keep the molten steel flow during filtration. This was due to the exothermic reaction of the filter surface and the molten steel. Also, the filter did not suffer from thermal shock or distortion during the test. These advantages will open the door for improved economic and efficient filtration of casting steel.

31. Mai 2002

31. Mai 2002

- 17 -

Claims:

1. A ceramic filter suitable for molten metal filtration comprising a bonded network of graphitized carbon and fibers.
- 5 2. The filter of claim 1, wherein the graphitized carbon constitutes up to 15 % by weight, in particular up to 10 % by weight, more specifically 5% by weight.
- 10 3. The filter of claim 1 or 2, wherein the fibers are selected from the group consisting of ceramic fibers, glass fibers, organic fibers, carbon fibers, metal fibers and mixtures thereof.
- 15 4. The filter of claim 3, wherein the ceramic fibers are selected from the group of alumina fibers, silica fibers, aluminosilicate fibers and mixtures thereof.
- 20 5. The filter of claim 3, wherein the organic fibers are selected from the group of polyester fibers, polyacrylonitrile fibers, polyethylene fibers, polyamide fibers, viscose fibers, aramid fibers, and mixtures thereof.
6. The filter of anyone of claims 1 to 5, characterized in that it contains an amount of 0,1 to 20, in particular 1 to 10 % by weight of said fibers.
- 25 7. The filter of anyone of claims 1 to 6, characterized in that the length of the fibers is in the range of 0.1 mm to 5 mm.
8. A method to produce ceramic filters according to anyone of claims 1 to 7, comprising the steps

- a) impregnating a foam made of thermoplastic material with a slurry containing fibers, a graphitizable carbon bonding precursor, ceramic powder, and optionally other additives,
 - b) drying, optionally followed by one or two coatings of the same slurry in order to increase the mass, followed by final drying,
 - 5 c) firing the impregnated foam in non-oxidizing and/or reducing atmosphere at a temperature in the range of from 500 to 1000 °C, in particular from 600 °C to 700 °C,
- whereby the carbon bonding precursor is converted at least partially or
- 10 fully to a bonded network of graphitized carbon and organic fibers undergo a pyrolysis.

9. The method of claim 8 utilizing a thermoplastic foam that contains polyurethane.

15

10. The method of claims 8 or 9 wherein the carbon bonded precursor is mixed with fibers, ceramic powder, water, organic binder, and additives to control the rheology, prior to impregnating the foam.

20 11. A method to produce the ceramic filters according to anyone of claims 1 to 7, comprising the steps

- a) pressing a semi-damp mixture comprising, fibers, ceramic powder and a graphitizable bonding precursor and optionally other additives in a hydraulic press,
- 25 b) pressing to obtain a perforated article in the shape of a disk or a block,
- c) firing the perforated article in non-oxidizing and/or reducing atmosphere at a temperature in the range of from 500 °C to 1000 °C, in particular from 600 °C to 700 °C,

whereby the carbon bonding precursor is converted partially or fully to a bonded network of graphitized carbon.

12. The method of any one of claims 8 to 11 wherein high melting
5 pitch (HMP) is used as the graphitizable carbon bonding precursor.

13. The method of any one of claims 8 to 12 wherein a slurry or semi-damp mixture is used comprising:

fibers in the range of 0,1 to 20 parts by weight,
10 graphitizable carbon bonding precursor in the range of from 2 to 15 parts by weight,
ceramic powder in the range of from 0 to 95 parts by weight,
anti-oxidation material in the range of from 0 to 80 parts by weight,
graphite in the range of from 0 to 90 parts by weight,
15 organic binder in the range of from 0 to 10, in particular 0.2 to 2 parts by weight and,
dispersion agent in the range of from 0 to 4, in particular 0.1 to 2 parts by weight.

20 14. The method of claim 13 wherein zirconia, silica, alumina, brown fused alumina, magnesia, any type of clay, talcum, mica, silicon carbide, silicon nitride and the like or a mixture thereof, or graphite, is used as the ceramic powder.

25 15. The method of claim 13 or 14 wherein metallic powders such as steel, iron, bronze, silicon, magnesium, aluminum, boron, zirconium boride, calcium boride, titanium boride and the like, and/or glass frits containing 20 to 30 weight percent of boric oxide are used as the anti-oxidation material.

30

16. The method of any one of claims 13 to 15 wherein a green binder such as PVA, starch, gums, sugar or the like or a combination thereof is used as the organic binder.

5 17. The method of any one of claims 13 to 16 wherein ligninsulphonate is used as the dispersion agent.

18. The method of any one of claims 13 to 17 wherein a slurry or semi-damp mixture is used that further comprises:

10 a plasticizer such as polyethylene glycol (molecular weight: 500 to 10000) in the range of from 0 to 2 parts by weight,
an anti-foam agent such as silicon anti-foam in the range of from 0 to 1 part by weight.

Abstract

5 **FIBER REINFORCED FILTER FOR MOLTEN METAL FILTRATION
 AND METHOD FOR PRODUCING SUCH FILTERS**

The present invention relates to a fiber reinforced ceramic filter for molten metal filtration that comprises a bonded network of graphitized carbon and a method for producing such filters.

10